

Aglime Analysis

Flint Rail Yard

6299 Bellview Street
Flint MI 48505

Stoneco Sales:

Telephone: (734) 241-8699 / Fax: (734) 241-3636

Gradation:

Sieve/Test	Percent Retained
3/8"	100.0
#4	99.1
#8	95.2
#16	76.3
#30	55.1
#50	40.8
#60	28.5
#100	31.5
#200	27.0
PAN	0.0
FM	2.02
Wash Loss (#200/75um)	25.9
Moisture	4.9
Calcium	18.90
Magnesium	10.59
CaCO3 Equivalent	85.06
Effective CaCO3 Equivalent	48.31