



## Stoneco of Michigan

15203 S. Telegraph Road  
Monroe, MI 48161  
(734) 241-8966  
[www.stoneco.net](http://www.stoneco.net)  
[www.aglime.com](http://www.aglime.com)

---

## Maybee

6837 Scofield Road  
Maybee, MI 48159

Moisture	6.67 %
Calcium	18.65 %
Magnesium	9.66 %
Total Neutralizing Power	81.33 %
% Retained #8	10.0 %
% Retained #20	23.0 %
% Retained #60	25.0 %
% Retained #100	9.0 %
Effective Neutralizing Power	1002 lbs/ton