



Stoneco of Michigan

15203 S. Telegraph Road
Monroe, MI 48161
(734) 241-8966
www.stoneco.net
www.aglime.com

Ottawa Lake

7555 Whiteford Road
Ottawa Lake, MI 49267

Aglime Analysis

Moisture	4.32 %
Calcium	19.57 %
Magnesium	11.02 %
Total Neutralizing Power	87.89 %
% Retained #8	1.0 %
% Retained #20	25.0 %
% Retained #60	39.0 %
% Retained #100	9.0 %
Effective Neutralizing Power	1114 lbs/ton

Stoneco of Michigan
Providing all of your Aglime,
Limestone, Sand and Gravel Needs.



Stoneco of Michigan

15203 S. Telegraph Road
Monroe, MI 48161
(734) 241-8966
www.stoneco.net
www.aglime.com

Ottawa Lake

7555 Whiteford Road
Ottawa Lake, MI 49267

Hi-Cal Aglime Analysis

Moisture	3.74 %
Calcium	29.70 %
Magnesium	5.62 %
Total Neutralizing Power	94.12 %
% Retained #8	3.0 %
% Retained #20	34.0 %
% Retained #60	30.0 %
% Retained #100	8.0 %
Effective Neutralizing Power	1088 lbs/ton

Stoneco of Michigan
Providing all of your Aglime,
Limestone, Sand and Gravel Needs.