



11/06/2018

2100-AG LIME Limestone

Ottawa Lake Pit # 58-003
Ag Lime

Procedure	Sieve/Test	Average	Unit
	3/8"	97.8	%
	#4	97.7	%
	#8	96.0	%
	#10	94.0	%
	#16	81.2	%
	#30	59.1	%
	#40	51.6	%
	#50	43.3	%
	#60	39.9	%
	#100	34.4	%
	#200	30.2	%
	Wash Loss (#200/75um)	29.7	%